URAI PAINTS
www.urpaints.com

Technical Data Sheet

ATM Acrylic Alkali Resisting Primer A1000

Bulletin no. .....

Description

An ultimate formula which developed from special acrylic resin to provide an exceptional property for alkali resistance on new surfaces. Easy to apply. Enhance the adhesion between substrates and top coating. Suitable for both of exterior and interior application.

Application

It is recommended for new surfaces priming to apply on both of exterior and interior. Excellent resistance against to alkali and fungus.

Technical Data

Product type	:	Acrylic Co-polymer
Appearance	:	Off white colour, viscous liquid.
Film type	:	Egg shell matt
Specific Gravity (water = 1)	:	1.4 – 1.5
Viscosity	:	105 – 110 KU at 25 °C
Application tools	:	Brush – Roller – Conventional spray
Drying time at 25 °C		
- Dry to touch	:	15 - 30 minutes.
- Dry to recoat	:	1 – 2 hours.

Painting System

Leaves new surfaces to be fully cured at least 1 month to avoid any damaging from efflorescence. Clean the surface to be free from dust, dirt, grease or any loose particles.

- Priming by ATM Acrylic Alkali Resisting Primer A1000 1 coat.

For Interior	Top coating by ATM Acrylic Emulsion Paint for INT	2-3 coats
For Exterior	Top coating by ATM Acrylic Emulsion Paint for EXT	2-3 coats

Coverage

35 – 40 sq.m/ gallon. /coat

Storage & Shelf life

Maximum 5 years in sealed container. Keep container in a cool dry and well-ventilated place. Protect from direct sunlight. When not in use, keep container tightly closed and use again after correct storage.

Safety, Health and Environment Information

Keep out of reach of children. Use in a well-ventilated area. Avoid contact with skin or eyes. Wash thoroughly after handling. If on skin, wash with plenty of soap and rinse skin with clean water. If in eyes, rinse cautiously with water for several minutes. Do not use empty container for food stuff. Do not empty into drains.

Packing

3.6 Litres and 18 Litres.

DISCLAIMER: *The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.*

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3) South Sathorn rd., Yannawaa, Sathorn, Bangkok 10120. Tel: +66 2 312 1049-50, +66 2 750 4808-9 Fax: +66 2 312 1163