URAI PAINTS
www.urpaints.com

Technical Data Sheet

GALANT GREY PRIMER no. 1040

Bulletin no. .....

Description

A speicialized formulation of grey primer based on modified alkyd resin and special quality pigments. It is designed to provide an excellent adhesion with quick dry. Good corrosion resistance and helps to enhance the adhesion between surface and top coating.

Application

Suitable to be using as primer for steel or metal surfaces such as handrail, grills for windows, curved steel, machines, etc.

Technical Data

Product type	:	Alkyd resin
Appearance	:	Viscous liquid in grey colour.
Film type	:	Egg shell matt
Specific Gravity (water = 1)	:	1.4 – 1.5
Viscosity	:	100 - 105 KU at 25 °C
Application tools	:	Brush, roller or spray
Diluent	:	Lobster Alkyd Enamel Thinner Lion brand turpentine substitute
Drying time at 25 °C		
- Dry to touch	:	15 - 30 minutes.
- Dry to recoat	:	4 - 6 hours.

Painting System

Surface preparation :

Make sure the surface to be painted is free from dust, dirt, grease, waxy contaminant and loose particles. Rust or millscales should be removed.

Primer coating :

- Galant Grey Primer no. 1040 — 1 – 2 coats
- Galant Alkyd Enamel — 2 – 3 coats

Coverage

8 - 12 sq.m/ litre /coat

Storage & Shelf life

Maximum 5 years in sealed container. Keep away from heat/ sparks/ open flames. No smoking. Keep container in a cool dry and well-ventilated place. Protect from direct sunlight. When not in use, keep container tightly closed and use again after correct storage.

Safety, Health and Environment Information

Keep out of reach of children. Use only outdoors or in a well-ventilated area. Wear protective gloves, eye and face protection. Avoid contact with skin or eyes. Wash thoroughly after handling. IF ON SKIN; Wash with plenty of soap and rinse skin with clean water. IF IN EYES, Rinse cautiously with water for several minutes. Do not empty into drains. Avoid release to the environment.

Packing

0.875 Litres, 3.5 Litres and 17.5 Litres.

DISCLAIMER: *The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.*

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3) South Sathorn rd., Yannawaa, Sathorn, Bangkok 10120. Tel: +66 2 312 1049-50, +66 2 750 4808-9 Fax: +66 2 312 1163