



LOBSTER Undercoat White No.1600

Bulletin no.

Description	LOBSTER undercoat white is formulated from acrylic resins and high quality of pigment. It is performed as intercoat for adhesion enhancement between substrate and top coat. Quick drying with high opacity finish. Excellent adhesion. Good fungus resistance.																		
Application	It is an ideal to be primer for wood substrate such as furniture, wood carving, door, window, fence, etc.																		
Technical Data	<table border="1"><tr><td>Product type</td><td>: Primer</td></tr><tr><td>Appearance</td><td>: Viscous liquid white colour.</td></tr><tr><td>Texture</td><td>: Eggshell</td></tr><tr><td>Specific Gravity (water = 1)</td><td>: 1.300-1.500</td></tr><tr><td>Solid content</td><td>: 60-80 %</td></tr><tr><td>Viscosity</td><td>: 100-105 KU at 25 °C</td></tr><tr><td>Application</td><td>: Brush, Roller or Spray Gun</td></tr><tr><td>Dilution</td><td>: LION Turpentine Substitute No. T-21 or LOBSTER Alkyd Enamel Thinner. Mixed in 10%</td></tr><tr><td>Drying time</td><td>: - Dry to touch 30 minutes - Dry to recoat 2 hrs.</td></tr></table>	Product type	: Primer	Appearance	: Viscous liquid white colour.	Texture	: Eggshell	Specific Gravity (water = 1)	: 1.300-1.500	Solid content	: 60-80 %	Viscosity	: 100-105 KU at 25 °C	Application	: Brush, Roller or Spray Gun	Dilution	: LION Turpentine Substitute No. T-21 or LOBSTER Alkyd Enamel Thinner. Mixed in 10%	Drying time	: - Dry to touch 30 minutes - Dry to recoat 2 hrs.
Product type	: Primer																		
Appearance	: Viscous liquid white colour.																		
Texture	: Eggshell																		
Specific Gravity (water = 1)	: 1.300-1.500																		
Solid content	: 60-80 %																		
Viscosity	: 100-105 KU at 25 °C																		
Application	: Brush, Roller or Spray Gun																		
Dilution	: LION Turpentine Substitute No. T-21 or LOBSTER Alkyd Enamel Thinner. Mixed in 10%																		
Drying time	: - Dry to touch 30 minutes - Dry to recoat 2 hrs.																		
Application Instruction	<ol style="list-style-type: none">Surface Preparation. Wood Surface<ul style="list-style-type: none">- Old wood surface: Flake surface must be eliminated. Remove splinter with sandpaper to enhance better adhesion.- New wood surface: Smooth a wood surface with sandpaper and cleaning the substrate to free from oil, grease and waxy contaminate.Priming Apply the LOBSTER undercoat white for priming the surface 1-2 coats by brush, roller or spray Gun. Drying time to recoat is 1-2 hrs. by approximately.Top Coating Apply LOBSTER Synthetic Resin Alkyd Enamel to top coat 2 coats.																		
Coverage	30 – 40 sq.m / gallon /coat																		



URAI PAINTS
www.urapaints.com

LOBSTER Undercoat White No.1600

Bulletin no.

Storage & Shelf life	Maximum 5 years in sealed container. Protect from sunlight. Keep container tightly closed when not in use and use again after correct storage. Keep it in well-ventilated place.
Safety, Health and Environment Information	<ul style="list-style-type: none">● Keep out of reach of children.● Keep away from heat/ sparks/ open flames. No smoking● Use in a well-ventilated area.● Avoid contact with skin or eyes.● If on skin, wash with plenty of soap and rinse skin with clean water.● If in eyes, rinse cautiously with water for several minutes.● Avoid release to the environment.
Packing	0.875 Litres / 3.5 Litres/ 17.5 Litres

DISCLAIMER: The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3)
South Sathorn rd., Yannawa, Sathorn,
Bangkok 10120.
Tel: +66 2 312 1049-50, +66 2 750 4808-9
Fax: +66 2 312 1163
www.urapaints.com