



ATM Chrome Spray Enamel

Bulletin no.

Description	ATM chrome spray enamel is a specially formulated from high quality of petroleum resin and selected pigment. That is premium quality spray paint to give look chrome finish. It is not real chrome, just looks like chrome and quick drying with excellent adhesion.																					
Application	It is ideal to make a basic item to be elegant in seconds. More luxury in appearance. Great for decoration to crafts, furniture or artworks.																					
Technical Data	<table border="1"><tr><td>Product type</td><td>:</td><td>Petroleum Resin</td></tr><tr><td>Appearance</td><td>:</td><td>Colour liquid spray regarding to catalog.</td></tr><tr><td>Film type</td><td>:</td><td>Gloss</td></tr><tr><td>Viscosity (Ford cup # 4)</td><td>:</td><td>12-14 sec at 25 °C (In liquid state)</td></tr><tr><td>Flash point</td><td>:</td><td>-73 °C (Based on the lowest flash point material, spray propellant (LPG – Liquefied Petroleum Gas))</td></tr><tr><td>Air vapour pressure</td><td>:</td><td>4.5 – 5 kg/cm² at 30 °C</td></tr><tr><td>Drying time</td><td>:</td><td>- Dry to touch 15 minutes - Dry to recoat 1 hours</td></tr></table>	Product type	:	Petroleum Resin	Appearance	:	Colour liquid spray regarding to catalog.	Film type	:	Gloss	Viscosity (Ford cup # 4)	:	12-14 sec at 25 °C (In liquid state)	Flash point	:	-73 °C (Based on the lowest flash point material, spray propellant (LPG – Liquefied Petroleum Gas))	Air vapour pressure	:	4.5 – 5 kg/cm ² at 30 °C	Drying time	:	- Dry to touch 15 minutes - Dry to recoat 1 hours
Product type	:	Petroleum Resin																				
Appearance	:	Colour liquid spray regarding to catalog.																				
Film type	:	Gloss																				
Viscosity (Ford cup # 4)	:	12-14 sec at 25 °C (In liquid state)																				
Flash point	:	-73 °C (Based on the lowest flash point material, spray propellant (LPG – Liquefied Petroleum Gas))																				
Air vapour pressure	:	4.5 – 5 kg/cm ² at 30 °C																				
Drying time	:	- Dry to touch 15 minutes - Dry to recoat 1 hours																				
Application Instruction	<p>Surface Preparation</p> <p>The surface should be clean and dry. If there are oil or waxy contaminate must be cleaned off before priming.</p> <p>Priming</p> <p>Priming by ATM spray acrylic lacquer No. A 210 for 2 coats. Drying time to recoat 10 minutes by approximately.</p> <p>Coating</p> <ul style="list-style-type: none">● Shake ATM chrome spray enamel can thoroughly 2 minutes before using and shake periodically during spray.● Spray from a distance of about 1 foot.● For better result apply several thin coatings with an interval of 15 minutes.● After spraying turn can upside down and press spray head to clean the spray nozzle.																					
Coverage	1.2-1.5 sq.m / coat / can (270 g)																					
Storage & Shelf life	Maximum 1 year in sealed container. Protect from sunlight. Do not expose to temperatures exceeding 25-30 °C. Keep it in well-ventilated place.																					



URAI PAINTS
www.urapaints.com

ATM Chrome Spray Enamel

Bulletin no.

Safety, Health and Environment Information

- Keep out of reach of children.
- Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.
- Use in a well-ventilated area.
- Do not spray on an open flame or other ignition source.
- If on skin, wash with plenty of soap and rinse skin with clean water.
- If in eyes, rinse cautiously with water for several minutes.
- Do not pierce or burn, even after use.
- Avoid release to the environment.

Packing

226 g (C180 and C980) / 270 g (C180)

DISCLAIMER: *The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.*

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3)
South Sathorn rd., Yannawa, Sathorn,
Bangkok 10120.
Tel: +66 2 312 1049-50, +66 2 750 4808-9
Fax: +66 2 312 1163
www.urapaints.com