

# ATM Acrylic Wall Putty No.107

<b>Description</b>	ATM wall putty no.107 is a ready-to-use product. It is formulated from special acrylic for using as a filler on crack or hole surfaces. It gives smooth surface with good adhesion, no sagging and no stains after application. Quick dry with high durability. Easy to clean up.																
<b>Application</b>	Suitable to apply on surface of concrete, plaster, brick, ceramic, tiles or wood for both of exterior and interior.																
<b>Technical Data</b>	<table border="1"> <tr> <td>Product type</td> <td>: Acrylic Polymer</td> </tr> <tr> <td>Appearance</td> <td>: White colour paste</td> </tr> <tr> <td>Viscosity</td> <td>: 240,000 – 320,000 cps at 25 °C</td> </tr> <tr> <td>Specific gravity (water=1)</td> <td>: 1.500-1.800 at 25 °C</td> </tr> <tr> <td>pH</td> <td>: 9 - 10</td> </tr> <tr> <td>Mixing ratio</td> <td>: Ready to use</td> </tr> <tr> <td>Application</td> <td>: Trowel</td> </tr> <tr> <td>Drying time at 25 °C</td> <td>: Dry to touch 1 hr. Dry to scrub 2 hr. Dry to recoat 24 hr.</td> </tr> </table>	Product type	: Acrylic Polymer	Appearance	: White colour paste	Viscosity	: 240,000 – 320,000 cps at 25 °C	Specific gravity (water=1)	: 1.500-1.800 at 25 °C	pH	: 9 - 10	Mixing ratio	: Ready to use	Application	: Trowel	Drying time at 25 °C	: Dry to touch 1 hr. Dry to scrub 2 hr. Dry to recoat 24 hr.
Product type	: Acrylic Polymer																
Appearance	: White colour paste																
Viscosity	: 240,000 – 320,000 cps at 25 °C																
Specific gravity (water=1)	: 1.500-1.800 at 25 °C																
pH	: 9 - 10																
Mixing ratio	: Ready to use																
Application	: Trowel																
Drying time at 25 °C	: Dry to touch 1 hr. Dry to scrub 2 hr. Dry to recoat 24 hr.																
<b>Application Instruction</b>	<p><b>Surface Preparation</b></p> <p>The substrate should be clean, free from dust and dirt. Free from algae and fungus, without any traces of oil, laitance and curing compound.</p> <p><b>Application</b></p> <ul style="list-style-type: none"> <li>- Apply ATM wall putty no.107 on prepared surface by let it to be on the bottom of cracks or holes to avoid any cavity.</li> <li>- For cracks or holes in big size, should be applied by layer to layer. Leave the applied layer is dry before next layer will be done.</li> <li>- Let it dry by leaving about 2-3 hours. Smooth the surfaces by using fine sandpaper before top coating.</li> <li>- Top coat should be applied after 24 hours left.</li> </ul>																

<b>Application Instruction (continue)</b>	<b>Recommendations</b> <ul style="list-style-type: none"> <li>- Water could be added if necessarily.</li> <li>- Do not apply to hot surface. Protect area from strong sunlight to avoid cracking or any deteriorated from rapid water evaporation.</li> <li>- Do not apply to surface that structure is still movement or cracked.</li> <li>- Do not use the product for floor coating.</li> <li>- No recommendation to use in the immersion area e.g. swimming pool, water tank, etc.</li> </ul>
<b>Coverage</b>	0.5-1.0 kg / sq.m. / thickness of 1 mm
<b>Storage &amp; Shelf life</b>	Maximum 5 years in sealed container. Store in room temperature not over 35-40 °C. Protect from sunlight. Keep container tightly closed and keep it in a well-ventilated place.
<b>Safety, Health and Environment Information</b>	<ul style="list-style-type: none"> <li>● Keep out of reach of children.</li> <li>● Use personal protective equipment as required.</li> <li>● Use in a well-ventilated area.</li> <li>● If on skin, wash with plenty of soap and rinse skin with clean water.</li> <li>● If in eyes, rinse cautiously with water for several minutes.</li> <li>● Avoid release to the environment.</li> </ul>
<b>Packing</b>	0.4 kg / 1.5 kg / 5 kg / 25 kg