

U-90 Skim Coat Plus No.103

Version 1.0

www.urapaints.com

Date of issue 29.04.2022

Date of Issue 29.04.2022

Description	U-90 Skim coat plus no.103 is a skim smoothing rendering paste based on modified polymer design. It is ready to use for repairing surface defects, rendering thickness is 0.5-4.0 mm. It provides perfectly white smooth finish with excellent adhesion. Easy for sanding. Good trowel ability in multi-layers without cracks or peel off. Cost and time saving.																								
Application	Suitable for concrete, renders, cement board. Use for repairing, levelling uneven surface, eliminating the blemishes, seams or hairline crack. Idealized for both of interior and exterior.																								
Technical Data	<table> <tr> <td>Product type</td> <td>:</td> <td>Acrylic Polymer</td> </tr> <tr> <td>Appearance</td> <td>:</td> <td>Viscous liquid in white colour</td> </tr> <tr> <td>Viscosity</td> <td>:</td> <td>180,000 – 210,000 cps at 25 °C</td> </tr> <tr> <td>Specific gravity (water=1)</td> <td>:</td> <td>1.600-1.800 at 25 °C</td> </tr> <tr> <td>pH</td> <td>:</td> <td>8 - 10</td> </tr> <tr> <td>Solid content</td> <td>:</td> <td>78 – 85 %</td> </tr> <tr> <td>Mixing ratio</td> <td>:</td> <td>Ready to use</td> </tr> <tr> <td>Application</td> <td>:</td> <td>Trowel</td> </tr> </table>	Product type	:	Acrylic Polymer	Appearance	:	Viscous liquid in white colour	Viscosity	:	180,000 – 210,000 cps at 25 °C	Specific gravity (water=1)	:	1.600-1.800 at 25 °C	pH	:	8 - 10	Solid content	:	78 – 85 %	Mixing ratio	:	Ready to use	Application	:	Trowel
Product type	:	Acrylic Polymer																							
Appearance	:	Viscous liquid in white colour																							
Viscosity	:	180,000 – 210,000 cps at 25 °C																							
Specific gravity (water=1)	:	1.600-1.800 at 25 °C																							
pH	:	8 - 10																							
Solid content	:	78 – 85 %																							
Mixing ratio	:	Ready to use																							
Application	:	Trowel																							
Application Instruction	Surface Preparation The substrate should be clean, free from dust and dirt. Free from algae and fungus, without any traces of oil, laitance and curing compound. Application - Stir thoroughly and then, using trowel to apply small quantities of U-90 Skim coat plus on substrate to cover all required area. Leave the surface dry about 1-2 hours. - Using sandpaper to smooth the surface and clean the applied substrate to be free from dust and dirt. - Apply 2nd layer and rendering. Then, using sandpaper to smooth the surface again. Do cleaning the substrate before to next step. - Apply top coat after leave the surface to dry more than 24 hours. Recommendations - Do not apply to hot surface. Protect area from strong sunlight to avoid cracking or any deteriorated from rapid water evaporation. - Do not apply to surface that structure is still movement or cracked. - Do not use the product for floor coating.																								

U-90 Skim Coat Plus No.103

Version 1.0

www.urapaints.com

Date of issue 29.04.2022

	- No recommendation to use in the immersion area e.g. swimming pool, water tank, etc. - No dilution with water or any solvents.
Coverage	1 kg / sq.m. / thickness of 1 mm.
Storage & Shelf life	Maximum 4 years in sealed container. Store in room temperature not over 35-40 °C. Avoid UV exposure. Keep container tightly closed and keep it in a well-ventilated place.
Safety, Health and Environment Information	- Keep out of reach of children. - Use in a well-ventilated area. - If on skin, wash with plenty of soap and rinse skin with clean water. - If in eyes, rinse cautiously with water for several minutes. - Avoid release to the environment.
Packing	1.5 kg / 5 kg / 25 kg