

# U-90 Epoxy Putty (A+B) No.534

Description	<p>U-90 epoxy putty (A+B) no.534 is the two-part system adhesive consisting of epoxy resin putty (Part A) and hardener agent (Part B) by mixing ratio A:B is 1:1 (by weight). Good for repairing on cracked surface to give smooth finish. Effective crack sealing with durable adhesion.</p>																							
Application	<ul style="list-style-type: none"> <li>- Adhesive to join concrete to concrete.</li> <li>- Adhesive for surface injection parts.</li> <li>- Patching cracks in preparation for epoxy injection.</li> <li>- Filler for holes crack and other defects. Bolt and plate grouting.</li> </ul>																							
Technical Data	<table border="0"> <tr> <td>Product type</td> <td>:</td> <td>Epoxy Putty</td> </tr> <tr> <td rowspan="2">Appearance</td> <td>:</td> <td>Part A: viscous liquid in white colour</td> </tr> <tr> <td>:</td> <td>Part B: viscous liquid in light yellow colour</td> </tr> <tr> <td>Viscosity</td> <td>:</td> <td>250,000 – 300,000 cps at 25°C (Data of part A and part B)</td> </tr> <tr> <td>Specific gravity (water=1)</td> <td>:</td> <td>1.500-1.700 at 25°C (Data of part A and part B)</td> </tr> <tr> <td>Mixing ratio</td> <td>:</td> <td>Part A: Part B = 1:1</td> </tr> <tr> <td>Pot life</td> <td>:</td> <td>30-60 minutes (Depends of weather during operation)</td> </tr> <tr> <td>Appliance</td> <td>:</td> <td>Brush/ Trowel</td> </tr> </table>	Product type	:	Epoxy Putty	Appearance	:	Part A: viscous liquid in white colour	:	Part B: viscous liquid in light yellow colour	Viscosity	:	250,000 – 300,000 cps at 25°C (Data of part A and part B)	Specific gravity (water=1)	:	1.500-1.700 at 25°C (Data of part A and part B)	Mixing ratio	:	Part A: Part B = 1:1	Pot life	:	30-60 minutes (Depends of weather during operation)	Appliance	:	Brush/ Trowel
Product type	:	Epoxy Putty																						
Appearance	:	Part A: viscous liquid in white colour																						
	:	Part B: viscous liquid in light yellow colour																						
Viscosity	:	250,000 – 300,000 cps at 25°C (Data of part A and part B)																						
Specific gravity (water=1)	:	1.500-1.700 at 25°C (Data of part A and part B)																						
Mixing ratio	:	Part A: Part B = 1:1																						
Pot life	:	30-60 minutes (Depends of weather during operation)																						
Appliance	:	Brush/ Trowel																						
Application Instruction	<p><b>Surface Preparation</b></p> <p>Surface should be clean from dust, oil or grease, coating stains and all loose particles which may impact to surface adhesion.</p> <p><b>Application</b></p> <p>Epoxy putty is composed of two components. The mixing ratio is 1:1 (A+B) by weight. Pot life is 30-60 minutes. Leaves it dry for 3 days before use.</p> <p><b>Recommendation</b></p> <ul style="list-style-type: none"> <li>● Always wears personal protective equipment when using this product.</li> <li>● Clean up tools after use with water.</li> <li>● Keep a moderate quantity to mix up to get a best result.</li> </ul>																							

## U-90 Epoxy Putty (A+B) No.534

Coverage	0.5-1 sq.m / kg / thickness of 1 mm.
Storage & Shelf life	Maximum 1 year in sealed container. Store in room temperature not over 35-40 °C. Avoid UV exposure. Keep container tightly closed and keep it in a well-ventilated place.
Safety, Health and Environment Information	<ul style="list-style-type: none"><li>● Keep out of reach of children.</li><li>● Use in a well-ventilated area.</li><li>● If on skin, wash with plenty of soap and rinse skin with clean water.</li><li>● If in eyes, rinse cautiously with water for several minutes.</li><li>● Avoid release to the environment.</li></ul>
Packing	Part A – 0.5 kg / Part B – 0.5 kg